

LEVELEASE

Frequently Asked Questions

Kilsaran

KPRO
FLOOR

Questions

How many coats of primer do I need?

How much water do I add to the mix?

What is the shelf life of this product?

Can I add more water to make it go further?

Which Levelease product can I use over underfloor heating?

What is Levelease 250?

What is Levelease 225?

What is Levelease DUO 225?

What is Levelease 110?

Where can I use Levelease 250?

Where can I use Levelease 110?

Where can I use Levelease 225 and Levelease DUO 250?

Answers

All surfaces must be thoroughly primed before applying Levelease to ensure proper adhesion, flow, and prevent air bubbles. The exact number of coats depends on the porosity of the substrate.

Levelease 250/225/110: 4.0-4.3 litres of clean potable water per 20kg bag.

Levelease DUO 225: No additional water should be added. It must be mixed with the provided 4.6kg acrylic component.

9 months if stored in a dry, cool environment.

No, excess water may cause a loss of strength and performance.

Levelease 250, levelease 225, levelease DUO 225 and Levelease 110 are suitable.

A rapid hardening, fibre-reinforced cementitious levelling compound for internal use. Suitable for 2mm-50mm thickness applications.

A standard-setting, fibre-reinforced cementitious levelling compound for internal use. Suitable for 2mm-25mm thickness applications.

A Bi component self-levelling compound with a polymer liquid component, providing improved performance. Suitable for 2mm-25mm thickness applications.

A rapid hardening self levelling compound designed for smoothing uneven floors before installing final floor coverings. Ideal for both domestic and commercial projects, it creates a smooth, level surface from 0mm-10mm on concrete and screeded substrates.

Internally on sand and cement screeds, concrete, calcium sulphate screeds, heated screeds, ceramic tiles and plywood floors.

Internally on sand and cement screeds, concrete, calcium sulphate screeds and heated screeds.

Internally on sand & cement screeds, concrete, calcium sulphate screeds, heated screeds, and ceramic tiles.



Questions

Can I apply Levelease levelling compounds over painted floors?

Does Levelease require priming?

Can Levelease 225, Levelease 250 and Levelease DUO 225 be applied over ceramic tiles?

Is Levelease 225, Levelease 250, Levelease 110 and Levelease DUO 225 moisture tolerant?

Can Levelease be applied below a damp proof membrane?

Can I apply levelease direct to steel?

How long does Levelease 250 take to dry?

How long does Levelease 225 & DUO 225 take to dry?

How long does Levelease 110 take to dry?

How should I prepare my floor before using Levelease 250, Levelease 225, Levelease DUO 225 and Levelease 110?

How do I control moisture when installing Levelease?

How thick can Levelease 250 be applied?

How thick can Levelease 225 & DUO 225 be applied?

How thick can Levelease 110 be applied?

May I use Levelease 250, Levelease 225 Levelease 110 or Levelease DUO 225 externally?

Answers

This is not recommended as painted surfaces may prevent proper adhesion directly. The surface should be prepared appropriately with a gritty primer.

Yes, all Levelease products require acrylic or water-based primer to ensure adhesion and flow.

Yes as long as the tiles are clean, stable and properly primed.

Yes, it is moisture tolerant.

No, Levelease can be applied over a Damp Proof Membrane if additional water treatment is required as an underlayment before the final surface covering.

No, it is not recommended. The surface must be primed with gritty primer to apply over steel.

Light foot traffic in 2-3 hours. Impermeable floor coverings after 6-24 hours, depending on thickness.

Light foot traffic in 6 hours. Impermeable floor covering after 12-24 hours, depending on thickness.

Light foot traffic in 2-4 hours. Impermeable floor coverings after approximately 8-24 hours, depending on thickness.

Ensure the floor is clean, stable, dry and primed.

Ensure the substrate has a moisture level below 4% CM (6% TrameX/ Gravimetric weight percent). If those moisture levels are not this point, a treatment for moisture must be applied as such Levelease damp proof membrane.

2mm-50mm.

2mm-25mm.

0mm-10mm.

No, Levelease 250, 225, 110 and DUO 225 are designed for internal use only. They are not suitable for external applications as they are not formulated to withstand prolonged exposure to moisture, temperature variations, and weather conditions.

Get in touch:

ROI: T: 01 801 3484 www.kilsaran.ie | **UK:** T: 0161 872 8899 www.kilsaraninternational.co.uk

Place an Order: orders@kilsaran.ie **Customer Service:** csteam@kilsaran.ie

Tech Support: techsupport@kilsaran.ie

